

For best results **DRYLOK Extreme** should be well stirred and sprayed at room temperature (70 °F and 60% relative humidity). Conditions of high humidity and/or low temperature can cause poor results. It is recommended that a small test area be done before beginning the project.

Spray Recommendation:

Use Graco Ult 1095 (1 GPM) or larger Graco electric airless pump. For gas engine use Graco GMAX 3900 (1 GPM) or larger Graco Gas powered unit.

Either unit must have first 50' section of 3/8" x 50' airless hose, connecting to second section a 1/4" x 50' airless hose to a Silver Plus Gun using a 0.031 Graco airless tip. Use either a 30 mesh manifold filter or no filter at all.

Airless pressure must be 3000 psi.

Spray cross hatching patterns with two coats building to a 14 to 16 wet mil thickness.

United Gilsonite Laboratories does not recommend air spray application for this product.